

TESTS CONDUCTED

SUPERIOR
— UPHOLSTERY VINYL —

Wear/Performance

ASTM D 751 79 Weight (+/-10%OZ/Lin Yd)	30
ASTM D 751 Thickness (+/-10%mm)	0.90
ASTM D 751 Tensile Strength (LBS)	
WARP	80
WEFT	70
ASTM D 751 Tear Strength (LBS)	No Effect; Superior Chemical Resistance
WARP	6
WEFT	6
Surface Abrasion	50000
ASTM D 191A-5874 Cold Crack (-10°F)	Pass
QUV-B	Pass
Oil/Sulfide Stain Resistance	Superior Soil Resistance
ASTM G21 Fungus Resistance	No Growth; Superior Fungal Resistance
ASTM E1428	Super Stain Resistant
AATCC 164-01 NO2	Superior Colorfastness

Flammability

ASTM E648 Critical Radiant Flux	Class 1
ASTM E662 Optical Smoke Density	Passes
FMVSS 302 / CAL 117 SECTION E	Passes
ASTM C-518 R-Factor	Allows Radiant Heat

Individual test results are held at our manufacturing facility and can be provided if required.
All tests were completed by a certified independent laboratory.